

TECHNICAL FEATURES

Norma Standard	Caratteristiche Features	Valori Prescritti Value Required	Matera
ISO 10543/3	Assorbimento d'acqua Water absorption	≤3%	0,5% surface 4% global
ASTM C373		≤3%	0,5% surface 4% global
ISO 10545/9	Resistenza agli sbalzi termici Thermal shock	Nessuna alterazione visibile No visible alteration	Conforme According to
ASTM C484	Thermal shock	Unaffected	Unaffected
ISO 10545/13	Resistenza agli attacchi chimici Chemical Resistance	Nessuna alterazione visibile No visible alteration	Resiste Resistant
ASTM C650	Chemical Resistance	No visible alteration	Unaffected
UNE-ENV12633:2003	Resistenza allo scivolamento (R) Slip Resistance classification (R)		R10
UNE-ENV12633:2006	Resistenza allo scivolamento (CL) Slip Resistance classification (CL)		CLASSE 3 Rd>45
ANSI A326.3:2022	Determination of Dynamic Coefficient of Friction (DCOF)	Before 0,30 After 0,29	Before 0,80 After 0,80

PACKING

Formato Size	Pcs Sqm	Box Pallet	Pcs Box	Kg Box	Kg Pallet	Sqm Pallet
5,5x13,5	134,68	108	56	9,95	1087,00	44,93
5,5x27	67,34	108	28	10,19	1112,00	44,91
5,5x27 chevron A	67,34	56	48	17,67	1001,00	39,93
5,5x27 chevron B	67,34	56	48	17,67	1001,00	39,93
5,5x27 chevron	67,34	56	96	17,67	1001,00	39,93
14x16 esagono	58,79	102	24	10,11	1043,00	41,64
20x20	25,00	60	20	18,70	1134,00	48,00

Descrizione prodotto e suggerimenti di posa: gres cotto ad alta temperatura (argille refrattarie) e realizzato in tutta massa con indurenti (chamotte). Il prodotto è trattato idrooleorepellente in suerficie e dopo la posa e stuccatura si consiglia un passaggio in superficie con prodotto FILA W68 o similare di altra marca.
Tutti i collanti per il gres porcellanato sono indicati e si consiglia stucco a base cementizia in tono.

Product description and installation suggestions: stoneware fired at high temperatures (refractory clays) and built in full body with hardeners (chamotte). The product is treated with water and oil repellent on the surface and after laying and grouting we recommend a coat on the surface with FILA W68 or similar product from another brand. All adhesives for porcelain stoneware are suitable and matching cement-based grout is recommended.

Classificazione secondo lo standard UNI EN 87: Group AI-AIIa
Metodo di formatura e grado di assorbimento d'acqua 0<AI-AIIa≤6%

*Classification in accordance with standard UNI EN 87: Group AI-AIIa
Shaping method extrusion with water absorption 0<AI-AIIa≤6%*

Destinazione d'uso finitura matt: outdoor-indoor, rivestimenti e pavimenti
Intended use matt finish: outdoor-indoor, wall-floor coverings